



SOLUTIONS

ENVIRONMENTAL PROTECTION, INC.

9939 US-131 South NE
Mancelona, Michigan
49659

Toll-Free 800-OK-LINER

www.geomembrane.com

20 mil PVC Geomembrane Specifications

TYPICAL APPLICATIONS:

Reservoirs

Canals

Sewage Lagoons

Landfill Closures

Soil Remediation

Farm Ponds

Water Features

Irrigation Ponds

Golf Course Ponds

Heap Leach Pads

Industrial Waste Ponds

Oil Drilling Reserve Pits

PVC liners fabricated by EPI are a single-ply construction with Polyvinyl Chloride as the principle polymer. Only first quality virgin resins are used and all materials meet or exceed the requirements of ASTM D-7176 Standard Specification for PVC geomembranes used in buried applications.

EPI utilizes statistical process control (SPC) to ensure the integrity of each panel produced. Samples from actual factory seams are removed during the welding process for a rigorous, proven testing procedure that assures you of the highest quality factory-fabricated PVC geomembranes available.

PVC Liners are fabricated by EPI in panels, accordion-folded in both directions, and packaged for shipment to your site for quick, easy installation to save

Thickness ± 5%	ASTM D-5199	.020"
Specific Gravity (min)	ASTM D-792	1.20
Tensile (lb/in-width, min)	ASTM D-882	48
Elongation at Break (% min)	ASTM D-882	360
Modulus (lb/in-width, min)	ASTM D-882	20
Tear Resistance (lb/in, min)	ASTM D-1004	6
Resistance to Soil Burial (% change, max)	ASTM G-160	
1. Breaking Factor		5
2. Elongation At Break		20
3. Modulus at 100% Elongation		20
Impact Cold Crack (°C)	ASTM D-1790	-26
Dimensional Stability (% change, max)	ASTM D-1204 (212°F/15 min.)	4
Water Extraction (% max)	ASTM D-1239	0.15
Volatile Loss (% max)	ASTM D-1203(A)	0.90
Hydrostatic Resistance (psi, min)	ASTM D-751(A)	68
Plasticizer Min Ave Molec Wt	ASTM 2124	400
Factory Fabricated Seams:		
Peel Strength (lbs/in, min)	ASTM D-882	12.5
Shear Strength (lbs/in, min)	ASTM D-882	38.4

These data are based on tests believed to be reliable. However, these are laboratory tests that may not simulate actual use conditions. They are provided for your informational purposes only. No warranty, express or implied, including any other further warranty of fitness for a particular purpose or merchantability, is made by this promotional literature

Preserving water resources for future generations

Visit our Internet web site at
www.geomembrane.com